

## AccoForm<sup>®</sup> BIA

<b>General Description</b>	High purity sodium montmorillonite, selectively mined, consisting of micronized particles and supplied as a free-flowing powder.		
<b>Functional Use</b>	This high purity montmorillonite is specifically mined for use as a drainage, retention, and formation aid in the manufacture of paper products, especially fine paper grades. Best performance is achieved when used in combination with a medium to high molecular weight cationic or non-ionic flocculant.		
<b>Purity</b>	Principally composed of the clay mineral montmorillonite. Contains minor amounts of quartz, plagioclase, calcite, siderite and hematite.		
<b>Solubility</b>	Dispersible but insoluble in water or alcohol. One gram of clay produces a surface area greater than 750 sq. meters when fully dispersed.		
<b>Moisture</b>	7 - 14% as shipped	<b>Texture</b>	Soft, slippery
<b>Odour</b>	None	<b>Taste</b>	None
<b>CEC</b>	Typically 120 meq/100g	<b>Settleable</b>	15% maximum
<b>ISO TAPPI Brightness</b>	Typically 24	<b>pH</b>	9.5–11.0 @ 5% solids
<b>Wet Particle Size</b>	Minimum 99.0% finer than 300 mesh (53 microns)		
<b>Dry Particle Size</b>	Minimum 80.0% finer than 200 mesh (75 microns)		
<b>Chemical Formula</b>	Diocahedral smectite, an expanding layer silicate:  $(\text{Na,Ca})_{0.33} (\text{Al}_{1.67}\text{Mg}_{0.33})\text{Si}_4\text{O}_{10}(\text{OH})_2 \cdot n\text{H}_2\text{O}$		
<b>Elemental Composition</b>	Typical analysis – moisture free.		
	SiO <sub>2</sub> 56.20%	Na <sub>2</sub> O 2.63%	
	Al <sub>2</sub> O <sub>3</sub> 20.09%	CaO 1.77%	
	MgO 3.38%	K <sub>2</sub> O 0.16%	
	Fe <sub>2</sub> O <sub>3</sub> 13.64%		
	All metals are expressed as oxides, which are complexed in the mineral		
<b>Packaging</b>	5-ply multi-wall poly-lined bags 25kg net, 1,000kg bulk bag or bulk		

The information and data contained herein are believed to be accurate and reliable. AMCOL Paper Technologies makes no warranty of any kind and accepts no responsibility for the results obtained through application of this information.